



DEMILEC (USA) LLC.  
POLYURETHANE SYSTEMS MANUFACTURER

### Heatlok Soy 200: R-Value & U-Value @ different thickness

Thickness, in	Thickness, mm	R-Value, ft. <sup>2</sup> h°F/BTU	R-Value, Km <sup>2</sup> /W	U-Value, W/Km <sup>2</sup>
<b>ASTM C 518 Tested Values</b>				
1	25.4	7.0	1.23	0.81
<b>Calculated R-Values*</b>				
2	50.8	14.0	2.47	0.41
3	76.2	21.0	3.70	0.27
3.5	88.9	24.5	4.31	0.23
4	101.6	28.0	4.93	0.20
5.5	139.7	38.5	6.78	0.15
6	152.4	42.0	7.40	0.14
7.5	190.5	52.5	9.25	0.11
8.75	222.3	61.25	10.79	0.09
10	254	70	12.33	0.08

\*Calculated R-values are based on the result obtained at 1in thickness.

Prepared by:



Julija Sihanovic  
Polyurethane Chemist